

# REVIVAL

HARDWOOD FLOORING



Coefficient of Friction

# REVIVAL

HARDWOOD FLOORING

## Finish Testing Results

### Cross Hatch Test

	Test Reference	Trial: June 2015	Trial: July 2015	Trial: August 2015
<b>Cross Hatch Test</b> 5 Good - 1 Bad	ASTM D 3359	5	5	5

What this means to you: Our highly durable oil finish has superior adhesion properties with your wood flooring to provide you with a problem free floor for decades to come.

### Impact Test [N]

	Test Reference	Trial: June 2015	Trial: July 2015	Trial: August 2015
<b>Impact Test [N]</b>	EN 438-2	10	10	13

What this means to you: Our oil finish will not crack or flake and stays flexibly adhered to your floor. If you drop something and damage your floor, the finish will not add to the problem by cracking or flaking.

### Coefficient of Friction

Date	Device	Method	Result
7/10/2015	BOT-3000 1141	Wet Static	0.82
7/10/2015	BOT-3000 1141	Wet Static	0.75
7/10/2015	BOT-3000 1141	Wet Static	0.82
7/10/2015	BOT-3000 1141	Wet Static	0.79
7/10/2015	BOT-3000 1141	Wet Static	0.76
7/10/2015	BOT-3000 1141	Wet Static	0.82

Test by: TractionAuditing, the walkway surfaces auditing experts

Wet SCOF VALUE [ $\mu$ ]	Available Traction	Remediation
$\mu \geq 0.60$	High Traction, Low probability of slipping	Monitor SCOF regularly and maintain cleanliness to retain high traction

What this means to you: This floor has a very high resistance to a static, wet slip.